

# Flon-Chem® 1050-BLUE

is the new generation of microstructured, reinforced PTFE gasketing materials. Due to the very homogenous distribution of hollow glass microspheres, FLON-CHEM®-1050-BLUE gets its uniform density and a high adaptability. It assimilates to flange roughness and unevenness, applying just low gasket stress, and reduces surface diffusion to the minimum.



Low compressive creep and high stability lead to a reliable jointing. With this FLON-CHEM®-1050-BLUE is the optimum PTFE gasketing for all flanges with slightly damaged surfaces, distorted flanges, steel, metal alloy, glass, ceramic or plastic flanges, glass lined piping systems

## PRODUCT FEATURES:

Suitable for sealing all chemicals across the whole pH range (0–14) with the exception of molten alkali metals, fluorine gas, hydrogen fluoride or materials which may generate these.

Due to the very homogenous distribution of hollow glass Microspheres, **FLON-CHEM®-1050-BLUE** gets its uniform density and a high adaptability.

It assimilates to flange roughness and unevenness, applying just low gasket stress, and reduces surface diffusion to the minimum.

## FDA COMPLIANCE:

**FLON-CHEM®-1050-BLUE** complies with FDA Regulation 21 CFR 177.1550 for use in contact with food.

## AVAILABLE SIZE:

**FLON-CHEM®-1050-BLUE** is available in sheets size 1500mmx1500mm tolerance: +20/-0 and thickness 2 and 3 mm tolerance +/-10%, other thickness upon request.

**TYPICAL PROPERTIES:**

PROPERTIES	TEST METHOD	UNITS	VALUE
Colour			BLUE
Max Operating Temperature		°C	- 200 / + 260
Max Operating Pressure		bar	50
PxT		bar x° C	12000
Density	ASTM D792	gr/cm3	1,70 +/-0,05
Compression Modulus 23°C - 20 MPa KSW		%	25
Creep Relaxation 23°C - 1 MPa KSW	DIN 28090-2	%	6
Compression Modulus 150°C - 20 Mpa 16h WSW	DIN 28090-2	%	35
Creep relaxation 150°C - 1 Mpa - 16h WSW	DIN 28090-2	%	4
Tensile Stenght	ISO 13000-2	Mpa	> 13
Elongation at Break	ISO 13000-2	%	> 200
Compressibility	ASTM F36A	%	> 40
Recovery	ASTM F36A	%	> 35
Leackage rate	DIN 3535-6	mg(s-m)	< 0,01
Y ( 1,5 -3,0mm )	ASME VIII	MPa	11 - 17,5
m ( 1,5 - 3,0mm)	ASME VIII	factor	3 - 3,8

**ELECTRICAL PROPERTIES:**

PROPERTIES	TEST METHOD	UNITS	VALUE
Volume resistivity	ASTM D257	Ohm * cm	10 <sup>16</sup>
Surface resistivity	ASTM D257	Ohm	10 <sup>15</sup>

Note : These are typical properties and not used for specification purpose